

# Document made available under the Patent Cooperation Treaty (PCT)

International application number: PCT/US05/000753

International filing date: 11 January 2005 (11.01.2005)

Document type: Certified copy of priority document

Document details: Country/Office: US  
Number: 60/539,409  
Filing date: 27 January 2004 (27.01.2004)

Date of receipt at the International Bureau: 21 February 2005 (21.02.2005)

Remark: Priority document submitted or transmitted to the International Bureau in compliance with Rule 17.1(a) or (b)



World Intellectual Property Organization (WIPO) - Geneva, Switzerland  
Organisation Mondiale de la Propriété Intellectuelle (OMPI) - Genève, Suisse

1282189

# THE UNITED STATES OF AMERICA

TO ALL TO WHOM THESE PRESENTS SHALL COME:

UNITED STATES DEPARTMENT OF COMMERCE

United States Patent and Trademark Office

*February 07, 2005*

**THIS IS TO CERTIFY THAT ANNEXED HERETO IS A TRUE COPY FROM THE RECORDS OF THE UNITED STATES PATENT AND TRADEMARK OFFICE OF THOSE PAPERS OF THE BELOW IDENTIFIED PATENT APPLICATION THAT MET THE REQUIREMENTS TO BE GRANTED A FILING DATE.**

**APPLICATION NUMBER: 60/539,409**

**FILING DATE: *January 27, 2004***

**RELATED PCT APPLICATION NUMBER: *PCT/US05/00753***



Certified by

Under Secretary of Commerce  
for Intellectual Property  
and Director of the United States  
Patent and Trademark Office

012704

22764 U.S. PTO

PTO/SB/16 (01-04)

Approved for use through 07/31/2006. OMB 0651-0032  
U.S. Patent and Trademark Office; U.S. DEPARTMENT OF COMMERCE

Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it displays a valid OMB control number.

**PROVISIONAL APPLICATION FOR PATENT COVER SHEET**

This is a request for filing a PROVISIONAL APPLICATION FOR PATENT under 37 CFR 1.53(c).

Express Mail Label No. EV113109256US

22264 U.S. PTO  
60/539409

012704

INVENTOR(S)					
Given Name (first and middle [if any])		Family Name or Surname		Residence (City and either State or Foreign Country)	
Jay		Duffner		Winchester, MA 01890	
Additional inventors are being named on the _____ separately numbered sheets attached hereto					
TITLE OF THE INVENTION (500 characters max)					
PROCESS FOR REMOVING MICROBUBBLES FROM A LIQUID					
Direct all correspondence to: CORRESPONDENCE ADDRESS					
<input checked="" type="checkbox"/> Customer Number: 29621					
OR					
<input type="checkbox"/> Firm or Individual Name					
Address					
Address					
City		State		Zip	
Country		Telephone		Fax	
ENCLOSED APPLICATION PARTS (check all that apply)					
<input checked="" type="checkbox"/> Specification Number of Pages 15					
<input type="checkbox"/> Drawing(s) Number of Sheets					
<input type="checkbox"/> Application Data Sheet. See 37 CFR 1.76					
<input type="checkbox"/> CD(s), Number					
<input type="checkbox"/> Other (specify)					
METHOD OF PAYMENT OF FILING FEES FOR THIS PROVISIONAL APPLICATION FOR PATENT					
<input type="checkbox"/> Applicant claims small entity status. See 37 CFR 1.27.					
<input type="checkbox"/> A check or money order is enclosed to cover the filing fees.					
<input checked="" type="checkbox"/> The Director is hereby authorized to charge filing fees or credit any overpayment to Deposit Account Number: 501-908					
<input type="checkbox"/> Payment by credit card. Form PTO-2038 is attached.					
FILING FEE Amount (\$) 160.00					
The invention was made by an agency of the United States Government or under a contract with an agency of the United States Government.					
<input checked="" type="checkbox"/> No.					
<input type="checkbox"/> Yes, the name of the U.S. Government agency and the Government contract number are: _____					

Respectfully submitted,

[Page 1 of 2]

Date 01/27/04

SIGNATURE

REGISTRATION NO. 38204

TYPED or PRINTED NAME Timothy J. King

(if appropriate)

TELEPHONE (978) 436-6582

Docket Number: 200300086P2

**USE ONLY FOR FILING A PROVISIONAL APPLICATION FOR PATENT**

This collection of information is required by 37 CFR 1.51. The information is required to obtain or retain a benefit by the public which is to file (and by the USPTO to process) an application. Confidentiality is governed by 35 U.S.C. 122 and 37 CFR 1.14. This collection is estimated to take 8 hours to complete, including gathering, preparing, and submitting the completed application form to the USPTO. Time will vary depending upon the individual case. Any comments on the amount of time you require to complete this form and/or suggestions for reducing this burden, should be sent to the Chief Information Officer, U.S. Patent and Trademark Office, U.S. Department of Commerce, P.O. Box 1450, Alexandria, VA 22313-1450. DO NOT SEND FEES OR COMPLETED FORMS TO THIS ADDRESS. SEND TO: Mail Stop Provisional Application, Commissioner for Patents, P.O. Box 1450, Alexandria, VA 22313-1450.

If you need assistance in completing the form, call 1-800-PTO-9199 and select option 2.

## PROCESS FOR REMOVING MICROBUBBLES FROM A LIQUID

This invention relates to a process for removing microbubbles from a liquid. More particularly, this invention relates to a process for removing microbubbles from a liquid by filtration.

Top antireflective coating (TARC) is used in photolithography to attenuate photons reflected from a resist/air interface during exposure of the resist to a light pattern. The thin TARC/ film alters the phase of photons reflected from the TARC/air interface by 180° relative to the photon reflection from the TARC/resist interface. These light waves destructively interfere, reducing the energy from this reflection and thus reducing variation in light intensity through the thickness of the resist. Line width resolution can be improved and undesirable steps in the resist sidewall can be reduced by application of a TARC film.

TARC is dispensed onto a spinning wafer after deposition of photoresist or soft bake. The TARC fluid is an acidic aqueous preparation of a fluorinated surfactant sometimes accompanied by an organic polymer. The surfactant lowers the surface tension of the TARC fluid, giving the coating better uniformity, but contributes to the severity of microbubble defects. Microbubbles comprising stable gas bubbles generally less than 10 $\mu$ m in diameter, are the major contributor to defects in TARC films. Microbubbles in TARC solutions lead to defects in TARC films such as those deposited on a photoresist film utilized to form electrically conductive pathways on electronic components.

A surfactant in a liquid forms a skin around a microbubble at the gas/liquid interface. The surfactant can change the surface tension at the gas/liquid interface by moving between the bulk liquid and the gas/liquid interface. Variable surface tension allows microbubbles to change radius which prevents microbubbles from collapsing under shear stress and pressure fluctuations. In addition, the surfactant skin acts as a barrier to mass transfer of gas from the bubble to the surrounding liquid so that pressurization of the liquid may not result in re-dissolving of gas into the surrounding liquid. The ability to change shape and the reduced rate of gas dissolution allow surfactant-stabilized microbubbles to persist once they form in solution.

The distinction between a bubble and a microbubble is based on size. Bubbles and microbubbles are less dense than the liquid in which they exist and, given time, will rise to the surface of the liquid. The rate at which a bubble will rise is dependent on the liquid's viscosity and the bubbles diameter. This phenomenon is expressed by applying Stoke's law

for gasses in water. Table 1 gives the rising velocity in water for a bubble of given diameter.

a 1 $\mu$ m bubble will take nearly 7 days to rise from the bottom to the top of a 30cm tall container and

- a 100 $\mu$ m bubble will rise to the same surface in only 55 seconds.

While bubbles will rise to the liquid/air interface in the matter of minutes, microbubbles will persist in liquids for hours or days. In addition, bubbles and microbubbles in TARC solutions containing surfactant will take longer to rise than in pure fluids of equivalent viscosity due to drag forces created by the surfactant coating on the microbubbles.

Table 1- Rising velocity of bubbles in water at 20°C according to Stokes's Law.

Bubble Diameter	Rising Velocity cm/sec
0.1 $\mu$ m	5.437E-07
1 $\mu$ m	5.437E-05
10 $\mu$ m	0.00544
100 $\mu$ m	0.544
1,000 $\mu$ m	54.37

Bubbles and microbubbles are formed in liquids when the solubility of dissolved gasses decreases. Pressure fluctuations, such as those created during fluid pumping, can cause the formation of bubbles and microbubbles by several different mechanisms. Homogeneous nucleation, heterogeneous nucleation and cavitation are proposed mechanisms in literature for the formation of bubbles and microbubbles. Homogeneous nucleation results in the formation of microbubbles throughout a liquid when gas molecules form clusters and grow to a defined size. This phenomenon occurs when supersaturated dissolved gas in a liquid suddenly becomes insoluble, for example, by a reduction in pressure. Homogeneous nucleation is rare and is not a likely mechanism for bubble and microbubble formation in TARC. Heterogeneous nucleation is defined as bubble growth that occurs on hydrophobic surfaces. Hydrophobic surfaces or particles act as catalysts for bubble and microbubble formation when gas solubility in a liquid is reduced. The third mechanism, cavitation, is characterized by bubble and microbubbles formation at nucleation sites caused by a sudden reduction in pressure of a moving fluid. Both heterogeneous nucleation and cavitation are the likely mechanisms for bubble and microbubbles formation in TARC.

Since microbubbles have very small rising velocities, they cannot be adequately removed by giving the microbubble time to rise to the top of a container or chamber. Also, surfactant coated microbubbles resist dissolution when under pressure due to slow mass transfer of gas to the liquid and the ability of these microbubbles to change shape.

Accordingly, it would be desirable to provide a process for removing microbubbles from a liquid, particularly a surfactant-containing liquid which does not depend upon microbubble movement to a liquid/gas interface. In addition, it would be desirable to provide such a process which removes a substantial amount of microbubbles from the liquid.

#### SUMMARY OF THE INVENTION

This invention is based upon the discovery that porous membrane substrates having their surface modified with amide-containing monomers are particularly suitable for filtering liquids including acidic TARC surfactant-containing solutions to remove microbubbles therefrom. It is preferred to utilize porous membrane substrates that are resistant to degradation by acidic liquid solutions. It has been found that surface modified membranes having a hydrophilic modified surface are particularly useful for removing microbubbles from acidic solutions and are mechanically stable in such solutions.

The present invention utilizes a surface modified membrane formed of a porous membrane substrate having an average pore size between about 0.01 microns and about 0.03 microns having its surface modified with amide groups. The amide groups are derived from polymerizable, cross-linkable amide containing monomers comprising either N, N-methylene bisacrylamide (MBAM) (cross-linker) alone or N, N-methylenebisacrylamide mixed with dimethylacrylamide (DMAM) (monomer) at a weight ratio of MBAM/DMAM of between about 1:0 to about 1:4, preferably between about 1:1 to about 1:3. Each repeating molecular unit of polymerized MBAM contains two amide groups while each repeating molecular unit of polymerized DMAM contains one amide group. By varying the weight ratio of MBAM/DMAM, one can control the concentration of amide moiety positioned on a polymer backbone. Thus, the relative polar interaction and non-polar interaction characteristics of a membrane can be controlled and optimized for a given photoresist composition. The MBAM/DMAM cross-linker/monomer composition is deposited on the surface of the substrate porous membrane with a polymerization initiator and then is polymerized and cross-linked in situ on the substrate. As a result, the entire surface including the pore surfaces is modified with the cross-linked amide composition to form a porous membrane having a desired ratio of amide to methylene moieties.

It also has been found that the surface modified porous membrane compositions of this invention are more effective in removing microbubbles, from a liquid composition particularly an acidic aqueous solution containing a polymer such as a fluoropolymer and a surfactant such as a fluorinated surfactant than is the unmodified porous membrane substrate even when the unmodified porous membrane substrate has an average pore size which is smaller than the average pore size of the surface modified porous membrane utilized in this invention. It has been found that these surface modified membranes are more stable against degradation by acidic solution as compared to polyamide membranes, such as Nylon 66.

#### DESCRIPTION OF SPECIFIC EMBODIMENTS

A representative TARC composition which is filtered with the surface modified porous membrane of this invention comprises an acidic aqueous preparation of a fluorinated surfactant sometimes accompanied by an organic polymer with a pH between about 2 and 3.

In accordance with this invention a polymeric porous membrane having the desired resistance against degradation by an aqueous solution such as a TARC solution is directly coated throughout its entire surface with a polymerized cross-linked amide containing monomer composition. The monomer is deposited on the surfaces of the polymeric porous membrane substrate by graft polymerization and/or by deposition of the cross-linked monomer. The desired deposition of the cross-linked monomer onto the polymeric porous membrane substrate is effected as a direct coating and does not require or utilize an intermediate binding chemical moiety. The term "polymeric porous membrane substrate" as used herein is meant to include polymeric compositions formed from one or more monomers. Representative suitable polymers forming the porous membrane include polyolefins such as polyethylene, polypropylene, polymethylpentene, high density polyethylene, ultrahigh molecular weight polyethylene (UPE) such as those prepared by the process of U.S. Patents 4,778,601 and 4,828,772 which are incorporated herein by reference and the like; polystyrene or substituted polystyrenes; fluorinated polymers including poly(tetrafluoroethylene), polyvinylidene fluoride or the like; polyesters including polyethylene terephthalate, polybutylene terephthalate or the like; polyacrylates; polycarbonates; vinyl polymers, such as poly vinyl chloride and polyacrylonitriles. Copolymers also can be employed such as copolymers of butadiene and styrene, fluorinated ethylene-propylene copolymer, ethylene-chlorotrifluoroethylene copolymer or the like. Generally the polymeric porous membrane substrate has an average pore size between about 0.005 and 0.05 microns and more usually between about 0.01 and 0.03 microns.

The polymerization and cross-linking of the polymerizable monomer to the porous membrane by grafting and/or deposition must be effected so that the surfaces of the porous membrane including the inner surfaces of the pores are coated with a cross-linked/grafted polymer. Preferably, the surfaces of the porous membrane are entirely coated. Therefore, in a first step, the porous membrane is washed with a solvent composition that does not swell or dissolve the porous membrane and which wets the surfaces of the pores such as a mixture of water and an organic solvent. Suitable water-solvent compositions for this purpose include methanol/water, ethanol/water, acetone/water, tetrahydrofuran/water or the like. The purpose of this wetting step is to assure that the cross-linker/monomer composition subsequently contacted with the porous membrane wets the entire surface of the porous membrane. This preliminary wetting step can be eliminated when the reagent bath described below itself functions to wet the entire surface of the porous membrane. This can be affected when the reagent both contains a high concentration of organic reactants, for example 15% by weight or higher. In any event, all that is required is that the entire porous surface be wet so that the polymerizable monomer wets the entire surface of the porous membrane.

Suitable polymerizable cross-linker/monomer compositions include MBAM either alone or mixed with DMAM at a weight ratio of MBAM/DMAM between about 1:0 to about 1:4, preferably between about 1:1 to about 1:3. An amide density (AD) value for a microporous membrane which contains amide functionalized polymers on its surfaces can be defined as:

$$AD = \frac{\text{\# of amide with substitute or non substitute groups in polymer repeat unit}}{\text{molecular weight of polymer repeat unit}}$$
The AD values for surface modified membrane of this invention with MBAM/DMAM weight ratios of 1:0 and 1:4 are 0.013 and 0.010 respectively. For comparison, the AD for a membrane made from nylon 66 polymer is 0.009.

Suitable initiators and cross-linking agents for the monomers set forth above are well known in the art. The monomer, polymerization initiator and cross-linking agent are contacted with the porous membrane as a mixture in a solvent which is compatible with the three reactants and the porous membrane so that the desired free radical polymerization and cross-linking is achieved without the formation of a significant amount of slowly extractable by-products and without the formation of colored products. If readily extractable by-products are formed, these can be removed by conducting a washing step in a suitable solvent subsequent to the coating step.



The particular solvent employed for the polymerizable monomer, polymerization initiator and cross-linking agent will depend upon the particular reactants employed and upon the particular polymer utilized to form the porous membrane. All that is necessary is that the reactants dissolve in the solvent and are capable of being reacted by free radical  
5 initiation in the solvent system and that the solvent does not attack the porous membrane substrate. Thus, the particular solvent system used will depend upon the reactants and porous membranes employed. Representative suitable solvents include water or organic solvents such as alcohols, esters, acetone or compatible aqueous mixtures thereof.

Generally, the polymerizable cross-linker/monomer mixture is present at a total  
10 concentration between about 1% and about 20%, preferably between about 3% and about 9% based upon the weight of the reactant solution. The polymerization initiator is present in an amount of between about 0.25% and about 2.5% by weight, preferably between 0.75% and 1.75% by weight based upon the total weight of the polymerizable cross-linker/monomer mixture.

15 Any conventional energy source for initiating free radical polymerization can be employed such as heating, ultraviolet light, gamma radiation, electron beam radiation or the like. For example, when free radical polymerization is initiated by heating, the reactant solution and the porous membrane are heated to a temperature at least about 60°C and up to the temperature at which undesirable bulk polymerization occurs in solution or at which the  
20 solvent begins to boil. For example, generally suitable temperatures when utilizing an aqueous solvent system between about 80°C. and about 95 °C, preferably between about 88°C and about 92 °C. The polymerization reaction should be effected for a time to assure that the entire exposed surface of the porous membrane is coated with the deposited polymer composition but without plugging of the pores in the membrane. Generally, suitable  
25 reaction times are between about 0.1 and about 30 minutes, preferably between about 1 and about 2 minutes. Reaction can be effected while the porous membrane is immersed in solution. However, this will result in the polymerization of the monomer throughout the solution. It is preferred to saturate the porous membrane with the reactant solution and to effect reaction outside of the solution so that monomer is not wasted. Thus, the reaction can  
30 be conducted batch wise or continuously. When operating as a continuous process, a sheet of porous membrane is saturated with the reactant solution and then transferred to a reaction zone where it is exposed to energy to effect the polymerization reaction.

A comparison of mean isopropyl alcohol (IPA) bubble points (or mean IPA flow pore pressure as described in ASTM method F316-80) of the surface modified porous

membranes utilized in this invention with Dev membrane is as follows: Optimizer Dev (catalog number CWUZ16EL1, Mykrolis Corporation) =50 psi, UPE(0.03 microns) DMAM/MBAM 1:1 = 85 psi. The surface modified membranes utilized in this invention have an IPA bubble point greater than 50 psi. IPA bubble point provides a good measure of the capacity of a porous membrane to retain particles by size exclusion removal.

The following examples illustrate the present invention and are not intended to limit the same.

#### Example 1

Several filter membranes were chosen for study based on knowledge of bubble formation mechanisms and surfactant stabilized microbubble behavior. Membrane candidates with a range of particle retention (from 0.02 $\mu$ m to 0.1 $\mu$ m) and surface energy (hydrophobic or hydrophilic) were tested for their ability to lower microbubble level in a TARC fluid. Two sets of testing were performed to determine how retention rating and surface energy affect microbubble level in the liquid.

Laboratory experiments were conducted with an IntelliGen® 2 dispense system available from Mykrolis Corporation, Billerica, Massachusetts, USA and AZ Aquatar® TARC available from Clariant Corporation, Somerville, NJ, USA. A Particle Measuring Systems Liquilaz® SO<sub>2</sub> optical particle counter available from Particle Measuring Systems (PMS) Corporation, Boulder, CO, USA was installed on the dispense line. Figure 1 comprises a diagram of the experimental setup. The filters were primed with the TARC and the dispense procedure was continually performed until particle counts leveled off.

Figure 2 provides particle count results showing a reduction of microbubble level with more retentive filtration media. Particle counts include all counts sized >0.2 $\mu$ m. All membranes tested are flat sheet pleated membranes with the exception of 0.1 micron hollow fiber UPE. The data shows that filtration media retention efficiency has a large effect on microbubble level at steady state. The lowest level of microbubbles was provided by the 0.02 $\mu$ m UPE hydrophilic membrane.

The data shows that most “particles” being detected by the optical particle counter are bubbles and not particles because the particle distribution plotted on log-log axes is not linear. In Figure 3, cumulative particle counts are plotted vs. particle size. When only particles are present, cumulative particle count data forms a linear curve with a slope of -2 to -3.5 when plotted on log-log axes. Particle count data showing a knee and/or a lower slope indicates the presence of microbubbles. The data collected in this experiment has both characteristics.

A recirculation test stand was built to measure the microbubble level downstream of several types of filtration media after fluid has been left stagnant for a period of time, see Figure 4. A hydrophobic (low surface energy) UPE filter (LHVD) and a hydrophilic (high surface energy) UPE (PCM) filter were installed sequentially in the "Sample Filter"

5 location. The PCM surface is modified with a weight ratio of MBAM:DMAM of 1:0 prepared with 0.02 $\mu$ m UPE porous membrane substrate as described above. A Rion KL-20 optical particle counter (OPC) available from Rion Corporation, Ltd., Tokyo, Japan was installed downstream of the test filter to detect microbubbles. The pump was run until particle counts leveled off, at which point the pump was stopped. After two hours, the pump  
10 was restarted and the particle count downstream of the filter was measured.

The heterogeneous nucleation mechanism of bubble formation shows that hydrophobic materials will act as nucleation sites for microbubble formation. In Figure 5, the data show a large spike in particle counts for the hydrophobic filter after the resumption of flow. This spike is much more muted for the hydrophilic filter and particle counts  
15 quickly drop to low levels.

The 0.02 $\mu$ m rated hydrophilic UPE membrane provided the lowest level of microbubbles at steady state and after a stoppage of flow. This membrane was incorporated into the 0.02 $\mu$ m IMPACT Plus PCM filtration device.

The filter types tested were installed at a semiconductor manufacturing line in an effort to lower defects in top antireflective coating films. The experiment's goal was to find  
20 the type of filter that provided the lowest level of defects and to determine if lowered wafer-level defects would correlate with lower microbubble level as measured by optical particle counter.

The filters were installed in an RDS dispense system using AZ Aquatar TARC. The  
25 filters were installed and primed. TARC coated wafers were analyzed for defects with a KLA-Tencor AIT 2 available from KLA-Tencor Corporation, San Jose, CA, USA. The defect reduction trend revealed that filtration media retention efficiency and surface energy had a dramatic effect on wafer-level defects. The 0.02 $\mu$ m PCM membrane in the IMPACT Plus device was able to satisfactorily lower defect level in the TARC film. Use of the filter  
30 resulted in

- 57% reduction in defects compared to 0.04 $\mu$ m nylon membrane.
- 85% reduction in defects compared to 0.1 $\mu$ m nylon membrane.
- 88% reduction in defects compared to 0.1 $\mu$ m hollow fiber UPE (unmodified).

In a second semiconductor manufacturing line, a 0.05 $\mu$ m IMPACT Plus LHVD (unmodified UPE) was tested in parallel with a 0.02 $\mu$ m IMPACT Plus PCM porous membrane, a semiconductor wafer processing facility with NFC 540 TARC available from Japanese Scientific Rubber Corp. (JSR) of Sunnyvale, CA, U.S.A. Wafer level defects were measured with a KLA-Tencor SP1 available from KLA-Tencor Corporation, San Jose, CA, USA. The 0.02 $\mu$ m IMPACT Plus PCM (surface modified) proved to be an improvement over 0.05 $\mu$ m IMPACT LHVD in two ways. The PCM filter reduced defect counts by 50% and eliminated the occurrence of random spikes in defect level. Table 2 contains the data from this evaluation.

Table 2- Wafer level defect data in TARC film as measured by SP1.

Filter Name	Average Defect Level	Periodic Spike
0.05 $\mu$ m IMPACT LHVD	60-70 defects/wafer	250 defects/wafer
0.02 $\mu$ m IMPACT Plus PCM	30-40 defects/wafer	none

This data reveal the importance of selecting a hydrophilic, highly retentive filtration media for TARC filtration. The 0.02  $\mu$ m IMPACT Plus PCM provides the lowest level of on-wafer defects and prevented the occurrence of random spikes in defect level in top antireflective coatings.

#### Example 2

A surface modified UPE membrane is prepared from a hydrophobic microporous UPE membrane manufactured by Mykrolis Corporation and sold in the filter product (catalog number CWAY01). It has a rated average pore size of 0.03  $\mu$ m and an average thickness of 42 $\mu$ m.

The hydrophobic 0.03 $\mu$ m UPE membrane is unwound and passed through a membrane surface treatment to sequentially pre-wet with isopropyl alcohol (IPA) to prevent air locking in the pore, and then 20 wt.% hexylene glycol and 80% water solution.

After soaking in the hexylene glycol/water solution, the membrane is immersed into the polymerizable monomer and cross-linker mixture solution containing 0.3.% Irgacure 2959 (Ciba Specialty Chemical AG), 10% acetone, 3.5% N, N-methylenabisacrylamide, 86.2% water, all by weight. The monomer wet membrane is sandwiched between sheets of polyethylene (PE) film, and exposed to UV lamp "Fusion H bulb type" for each side of the membrane with the total of 4 UV lamps, followed by water rinsed, dried, and wound up on the core.

The resulting membrane is tested for wettability with water, water flow rate, mean isopropyl alcohol (IPA) bubble point and membrane thickness. Results are shown below:

-Water wet time (sec): 0.1 sec.

Water flow rate (ml/min/cm<sup>2</sup>): 1.2 @13.5 psi differential pressure and 21<sup>0</sup>C

5

-Thickness : 42 µm

-Mean IPA Bubble Point (ASTM method F316-80) : 85 psi

#### Example 3

10 Example 2 was repeated by using a monomer solution containing 4% MBAM, 4% DMAM, 10% acetone, Irgacure 0.75%.

The resultant membrane has the following properties:

-Water wet time (sec): 0.1 sec.

15

-Water flow rate (ml/min/cm<sup>2</sup>): 1.2 @13.5 psi differential pressure and 21<sup>0</sup>C

-Thickness: 42 µm

-Mean IPA Bubble Point (ASTM method F316-80): 86 psi

20

#### Example 4

This example provides a comparison of the composite porous membranes of this invention with a nylon 6,6 0.04 micron porous membrane and a composite membrane having a substrate comprising 0.05 microns UPE (Dev).

25

Table 3

Membrane	Monomer to Xlinker Wt. Ratio	Ion Exchange Capacity (IEC)***	
		Cation exchange (nmol/cm <sup>2</sup> )	Anion exchange (nmol/cm <sup>2</sup> )
Dev	3 to 1	18.5	20.2
Example 2	0 to 1	17.8	10.6
Example 3	1 to 1	17.7	13.1
0.04 Nylon 66	N/A	18.8	14.4
Pall Corporation Catalog No. MCD 924UNDEJ			

Note: the cation and anion exchange capacity (iec) are measured by a titration method using a METTLER TOLEDO- DL58 Autotitrator. Sodium hydroxide and silver nitrate solutions are used as reagents to determine the cation and anion iec respectively.

Table 4

Membrane	Hydrocarbon X to Amide -(CO-NR')- Ratio in Surface Polymer Repeat Unit	Membrane wet time with 10 wt.% Methanol/Water Solution
Dev	2.9:1	<1sec
Example 2	2.5:1	<1sec
Example 3	2.8:1	<1 sec
0.04 Nylon 66	5.0:1	<1sec

X = -CH<sub>2</sub>- or -CHR- or -CH<sub>3</sub>

R' = H or CH<sub>3</sub>

Example 5

This example provides a comparison of the composite porous membrane of this invention with a nylon 66 0.04 micron porous membrane and a composite membrane having a substrate comprising 0.05 microns UPE (Dev).

Table 5

Membrane	Monomer to Xlinker Wt. Ratio	Ion Exchange Capacity (IEC)***	
		Cation exchange (nmol/cm <sup>2</sup> )	Anion exchange (nmol/cm <sup>2</sup> )
Dev	3 to 1	18.5	20.2
Example 2	0 to 1	17.8	10.6
Example 3	1 to 1	17.7	13.1
0.04 Nylon 66	N/A	18.8	14.4
Pall Corporation Catalog No. MCD 924UNDEJ			

Note: the cation and anion exchange capacity (iec) are measured by a titration method using a METTLER TOLEDO- DL58 Autotitrator. Sodium hydroxide and silver nitrate solutions are used as reagents to determine the cation and anion iec respectively.

Table 6

5	Membrane	Hydrocarbon X to	Membrane wet time with 10 wt. %
		Amide -(CO-NR')- Ratio in	Methanol/Water Solution
		Surface Polymer Repeat Unit	
	Dev	2.9:1	<1sec
10	Example 2	2.5:1	<1sec
	Example 3	2.8:1	<1 sec
	0.04 Nylon 66	5.0:1	<1sec
15	X = -CH <sub>2</sub> - or -CHR- or -CH <sub>3</sub> R' = H or CH <sub>3</sub>		

20

25

30



## CLAIMS

1. A process for removing microbubbles from a liquid which comprises filtering said liquid with a composite porous membrane substrate having an average pore size between about 0.01 and 0.03 microns formed of a first polymer, said substrate being directly coated on its entire surface with a cross-linked second polymer formed from a monomer polymerized in situ with a free radical initiator and monomer composition comprising N, N-methylbisacrylamide (MBAM) optionally admixed with dimethylacrylamide (DMAM), said monomer composition being cross-linked in situ on said substrate, said composite porous membrane having essentially the same porous configuration as said porous membrane substrate.
2. The process of Claim 1 wherein the first polymer is ultrahigh molecular weight polyethylene.
3. The process of Claim 1 wherein the first polymer is polytetrafluoroethylene.
4. The process of any one of Claims 1, 2, or 3 wherein said liquid is an acidic top antireflective coating.
5. The process of any one of Claims 1, 2, or 3 wherein said liquid contains a surfactant.
6. The process of any one of Claim 4 wherein said liquid contains a fluoropolymer.
7. The process of any one of Claim 4 wherein said liquid contains a fluoropolymer and a surfactant.
8. The process of Claim 5 wherein said surfactant is a fluorinated surfactant.
9. The process of Claim 7 wherein said surfactant is a fluorinated surfactant.

ABSTRACT

A process is provided for removing microbubbles from a liquid by filtration with a composite porous membrane which is formed from a porous polymeric membrane having an average pore size between about 0.01 and 0.03 microns on which is directly coated a cross-linked polymer derived from N, N-methylenebisacrylamide (MBAM) optionally containing dimethylacrylamide (DMAM).